

Item	Unit	Value		Test Method
Base Fabric	Denier	300DX500D		(Domestic yarn) 100%PES
Construction	Weaving/inch	18x12		/
Weight of fabric	Gsm/m2	55±5		DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	455±5		DIN53352 BS3424 Method5B
Total weight	Gsm/m2	510±10		DIN53352 BS3424 Method5A
Thickness	mm	0.38±0.02		DIN EN ISO 2286-3
Width	cm	102---320		/
Tensile Strength	N/5cm	Warp	635	DIN53352 BS3424
		Weft	450	
Tearing Strength	N	Warp	70	DIN53356 BS3424
		Weft	65	
Adhesion	N/5CM	60		DIN53357 BS3425 Method9B
Temperature Resistance	℃	— 20～70		DIN53357 BS3425 Method10
Lacquering	None			
Flammability	Can be apply for: B2, NFPA701, DIN75200, etc.			
LOW CADMIUM & HEAVY METALS	We can be applied for : Cadmium free (EN71-3) or Reach Compliance			